TECHNICAL DATA SHEET



Autobond

Promast Autobond is an environmentally friendly, single-component, high-modulus MS Polymer Sealant for the automotive industry. With its unique fast curing and strong bonding features, Promast Autobond is preferred, especially in caravan assembly applications. It does not contain any solvents or isocyanat.

TECHNICAL DATA

	Basis	MS Polymer
	Consistancy	Stable Paste
-	Curing system	Moisture Curing
	Tack-free time	Ca. 5 mins
	Skin formation time * (20 °C / 65% R.H.)	Ca. 20 mins
	Curing speed * (20°C / 65% R.H.)	(2,5 - 3,5) mm /24h
-	Hardness (DIN 53505)	40 ± 5 Shore A
	Density	1,40 ± 0,05 g/ml
	Temperature resistance	-40 °C → 90 °C
	Max. tension (DIN 53504)	> 2,50 N/mm²
	Elasticity modulus 100% (DIN 53504)	> 0,70 N/mm ²
	Elongation at break (DIN 53504)	> 500%
	Application temperature	5 °C - 35 °C
-	Self life	15 Months

(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

APPLICATIONS AREAS

- Construction boards: Plywood, Laminated timber, OSB, Chipboard...
- · All vibrating metal joints of all types of vehicles.
- Window frames, doorsteps, decorative frames.
- Structural bonding in vibrating constructions.
- Insulation materials: Polystyrene, Mineral wool, Fiberglass, Polyurethane...
- Floor joints, stair steps, roof edges.
- Green-houses.

SPECIFICATIONS

- Fast curing 15 minutes after application.
- Non-staining on natural stones, marbles, granites and such substrates.
- Excellent adhesion to most materials such as metal, aluminum, glass, wood, stainless steel, copper, iron, brick, concrete, some plastics and their combinations...
- Excellent color stability, non-yellowing.• Not affected by surface moisture during curing, does not bubble.
- Does not contain any hazardous chemicals, odorless.
- High UV resistance.
- Over-paintable.
- Non-sagging.
- · Non-shrinking.
- Weatherproof.



TECHNICAL DATA SHEET AUTOBOND

REMARKS

- Promast Autobond may be overpainted with water-based paints, however, due to the large number of paints and varnishes available, we strongly suggest a compatibility test before application.
- The drying time of alkyd resin-based paints may increase.
- Promast Autobond can be applied to a wide variety of substrates. We recommend a preliminary compatibility test because specific substrates such as plastics, polycarbonate, etc, may vary from manufacturer to manufacturer.
- Promast Autobond can not be used as a glazing sealant.
- Not suitable for bonding aquariums.
- Promast Autobond can be used for bonding and sealing on natural stone.
- The sanitary formula should not replace regular cleaning of the joint. Excessive contamination, deposits, or soap remaining will stimulate the development of fungi.
- Do not use it in applications where continuous water immersion is possible.
- A total absence of UV can cause a color change in the sealant.
- When using different reactive joint sealants, the first joint sealant must be hardened entirely before the next one is applied.
- Promast Autobond has good UV resistance but can discolor under extreme conditions or after very long UV exposure.
- Discoloration may occur due to chemicals, high temperatures, and UV radiation. A change in color does not affect the technical properties of the product.
- Contact with bitumen, tar, or other plasticizer-releasing materials, such as EPDM, neoprene, butyl, etc., are to be avoided since they can give rise to discoloration and loss of adhesion.

CHEMICAL RESISTANCE

Good resistance to (salt)water, aliphatic solvents, hydrocarbons, ketones, esters, alcohols, diluted mineral acids and alkalis. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

SURFACE PREPERATION

Surfaces which contact with sealant must be clean and dry and not contain any oil, dust or rust. Non-porous surfaces must be cleaned in advance with a suitable solvent. Applied solvent must be wept well from the surface without allowing it to evaporate. Applying masking tape around the application joints prevents smudging and provides a more aligned application. Masking tape must be removed promptly after application. Primer is not needed before the application on non-porous surfaces like faience, ceramics and glass. Primer use may be required for some metal and plastic types.

APPLICATION METHOD

With manual - or pneumatic caulking gun.

PACKAGING (Volume)

290 ml cartridge 400 ml saussage 600 ml saussage

SHELF LIFE

15 months in unopened packaging in a cool and dry storage place at temperatures between $+5^{\circ}$ C and $+25^{\circ}$ C.

COLORS

White







Black









