

TECHNICAL DATA SHEET

CORNER BOND EXPRESS



Corner Adhesive

Polyurethane based corner joint adhesive used for bonding aluminum profiles. Fast curing, water resistant (D4) adhesive with strong adhesion features.

TECHNICAL DATA

■ Density	1,15 g/ml
■ Water and humidity resistance	D4
■ Open time	Ca. 10 mins.
■ Clamping time	Ca. 30 mins.
■ Shelf life	12 months

APPLICATIONS AREAS

- Aluminium brackets.
- Doors and windows.

SPECIFICATIONS

- Fast curing-low pressing time.
- Vertical and horizontal use. Non-sagging properties.
- Resistant to moisture, water and sea water-D4.
- Interior and exterior use.
- Transparent.
- Provides good adhesive strength with various substrates.

TECHNICAL DATA SHEET

CORNER BOND EXPRESS

REMARKS

- Since the open-time of the adhesive is very short clamping of the elements must be completed rapidly.
- When hardened, the color of the adhesive turns white.
- The adhesive must be spread on the substrates and applied as a thin layer.
- In applications below 10°C curing time will be prolonged.
- Full cure can take up to 12 hours.
- Dry substrates must be humidified with a wet cloth.

SAFETY INFORMATION

It contains isocyanate. If inhaled for long periods, it may cause sensitivity to respiratory organs. If the wet foam contacts the skin for long periods, it may cause local rash and sensitivity on the skin. For this reason, the environment should be well-ventilated during the application, contact with the skin should be avoided and protective gloves and safety goggles should be worn while working. Completely dried out PU adhesives do not carry risks to human health or to the environment.

SURFACE PREPERATION

Bonding surfaces must be clean and not contain oil, dirt, or lose parts. In addition, it must be made moist with water of ratio roughly 5% of adhesive quantity for surfaces that especially don't contain any moisture or they are moist-proof.

APPLICATION METHOD

- It should not be applied in temperatures below 5°C.
- Bonding substrates should be free of oil, dust, dirt, and loose particles.
- The adhesive should be applied as a thin layer in one of the bonding substrates.
- Non-porous and dry bonding substrates should be humidified with a wet cloth.

PACKAGING

310 ml cartridge x 25 pieces

290 ml cartridge x 25 pieces

SHELF LIFE

It should be stored in its closed package in a cool and dry environment between 5°C-25°C. When these conditions are met, it has a shelf life of 15 months from the date of production. The date of manufacture is indicated on the bottle.

COLOR



Opaque

Transparent



MANUFACTURER:
 PROMAST Kimya San. Tic. A.Ş. Ovacık Mh.
 Hacıoğlu Sk. No:21 B/0 41140 Başiskele
 KOCAELİ | TURKEY T: +90 (262) 335 41 82
 F: +90 (262) 335 41 83

